



AUTOCORE FC CrC

FCAW HARD FACING High Abrasion



SELF SHIELDED FLUX CORED WIRE FOR HIGH ABRASION APPLICATIONS

ALLOY BASIS:

C, Mn, Si, Cr

- Self shielded flux cored wire
- Excellent arc characteristics
- Low spatter

High percentage of Cr and C render highest resistance against gouging abrasion

WELDING POSITION:







DCEP

TYPICAL APPLICATIONS:

- Grinding rolls of cement mill and coal mill
- Table liners, coke chutes

Parts of earth moving and mining equipments

STORAGE / HANDLING:

Keep dry and follow handling instructions mentioned on the box

PHYSICAL PROPERTIES:		
Condition	Hardness, HRc	
As Welded	60-62	





PARAMETERS - PACKING DATA :				
Ø, mm	Voltage, V	Amperage, A	Kg/Spool	
2.4	25 - 31	200-350	12.5	
2.8	27 - 32	250-400	12.5	