

BETANOX DL

AWS A/SFA 5.4 E309L-16

STAINLESS STEEL (Dissimilar Steel Welding)

CLASSIFICATION:

ISO 3581-A
E 23 12L R 12

IS 5206
E 23.12 LR26

KEY FEATURES:

- Rutile type coating
- High ferrite content for highest resistance to cracking
- Low dilution on mild and low alloy steels due to higher alloy content
- Extra low carbon 23/12 type deposit
- Exhibit excellent corrosion and oxidation resistance upto 1100°C
- Suitable for all position
- Radiographic quality welds

APPROVALS: ABS/BV IRS/NPCIL/IBR/CE

TYPICAL APPLICATIONS:

- Dissimilar joints between stainless steels and low alloy or carbon steels
- Welding of AISI 309, 309L type steels
- For buffer layer on low alloy and carbon steels
- Joining corrosion resistant clad steels



TYPICAL CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt %:

C	Mn	Si	Cr	Ni
0.03	1.7	0.5	23.5	12.05

MECHANICAL PROPERTIES OF ALL WELD METAL:

	Condition	UTS, MPa	EL%	Ferrite No.
Typical	As Welded	560	36	12
Specification		520 min	30 min	15 max

PARAMETERS - PACKING DATA:

Ø x L, mm 2.0 x 300 2.5 x 350 3.15 x 350 4.0 x 350	Amperage, A 50-75 80-100 110-140 150-180	 AC (70 OCV) /DCEP REDRYING CONDITION: 250-300°C for minimum 1 hr.	All Positions, except vertical Downwards 
---	---	---	---

Available in Standard carton packing of 10 kg box containing 5 cartons of 2 kgs each.

EQUIVALENT:

GMAW	GTAW	FCAW	SAW	
			Flux	Wire
Miginox 309L	Tiginox 309L	Miginox FC 309L	Automelt S33	Subinox 309L