## **NICALLOY Mo-12**

CLASSIFICATION: ISO 14172 E Ni 6627 (NiCr21MoFeNb) -	<ul> <li>KEY FEATURES:</li> <li>Basic coated electrode</li> <li>Weld metal is highly resistant to hot cracking, stress corrosion cracking and thermal shock</li> <li>Works smoothly with negligible spatter</li> <li>Reduces carbon diffusion at high temperature</li> <li>Recommended for high temperature and creep resisting steels</li> </ul>			
APPROVALS: CE TYPICAL APPLICATIONS:				
<ul> <li>Joining materials of the same nature, e.g. material 2.4602 (NiCr21Mo14W) and these materials with low alloyed steels such as for surfacing on low alloy steels</li> <li>Welding components in chemical processes handling highly corrosive media</li> </ul>	<ul> <li>Dissimilar joints between Ni-Cr-Mo alloys and stainless, carbon or low alloy steels</li> <li>Overlay cladding on carbon, low alloy and stainless steels</li> <li>Digesters and paper making equipment, Scrubbers for flue gas desulphurization</li> </ul>			
TYPICAL CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt %:				

С	Mn	Si	Fe	Ni	Nb+Ta	Мо
0.017	2.0	0.5	66.5	20.9	1.6	9.3

## MECHANICAL PROPERTIES OF ALL WELD METAL:

	Condition	UTS, MPa	EL%
Specification	As Welded	650 min	35 min

PARAMETERS - PACKING DATA:				
<b>Ø x L, mm</b> 2.5 x 350 3.15 x 350	<b>Amperage, A</b> 45 - 70 80 - 100	AC (70 OCV)/DCEP	All Positions, except vertical Downwards	
4.0 x 350	90 - 130	<b>REDRYING CONDITION:</b> 250-300°C for minimum 1 hr.	<u> </u>	

Available in Ivory packing of 10 kg box containing 10 cartons of 1 kg each.



