

# TENALLOY 120G

AWS A/SFA 5.5 E12018-G

LOW ALLOY STEEL (High Temperature)

## CLASSIFICATION:

EN ISO 18275-A  
E 69 4 Z B 32 H5

## KEY FEATURES:

- Basic type coating
- Ni-Mn-Mo-Cr alloyed electrode
- Excellent crack resistance
- High strength and toughness at -50°C
- Radiographic weld quality

**APPROVALS:** CE

## TYPICAL APPLICATIONS:

- Welding of high tensile steels and fine grained steels like HY 80, HY 90, HY 100
- Joining high strength, low alloy or microalloyed steels to themselves or to lower strength steels, including carbon steels

## TYPICAL CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt %:



C	Mn	Si	Cr	Ni	Mo
0.06	1.75	0.4	0.35	2.1	0.3

## MECHANICAL PROPERTIES OF ALL WELD METAL:

	Condition	UTS, MPa	YS at 0.2% offset, MPa	EL%	CVN Impact at -50°C, J
Typical	As Welded	830 min	735-830	18 min	47 min
Specification					

Diffusible H<sub>2</sub> Content: <5 ml/100 gm

## PARAMETERS - PACKING DATA:

Ø x L, mm	Amperage, A		
2.5 x 350	60-90	 AC (70 OCV)/DCEP	All Positions 
3.15 x 350	100-140		
4.0 x 450	140-180		
5.0 x 450	190-250		
		<b>REDRYING CONDITION:</b> 250-300°C for minimum 1 hr.	

Available in Standard carton packing of 20 kg box containing 4 cartons of 5 kgs each. Also available in vacuum packing