

# TIGIL 80S-Ni1

**GTAW LOW ALLOY STEEL (Low Temperature)** 

## AWS A/SFA 5.28 ER80S-Ni1

#### **CLASSIFICATION:**

**EN ISO 636-A** W 55A 5U N2

#### **KEY FEATURES:**

- Copper coated low alloy steel solid filler wire & rod
- Typical 1%Ni-Mn alloy
- Uniform copper coating
- Medium strength weld deposit gives high impact at -45°C
- Radiographic quality weld

**APPROVALS:** ABS/BV/CE

#### **TYPICAL APPLICATIONS:**

- Welding of 1% Ni steels
- Welding fine grained and low alloyed Ni steels
- Welding of steels for application at sub-zero temperature

### TYPICAL CHEMICAL COMPOSITION OF BARE SOLID WIRE, Wt %:

С	Mn	Si	Ni
0.065	1.0	0.5	0.9

MECHANICAL PROPERTIES OF ALL WELD METAL:					
	Condition	UTS, MPa	YS at 0.2% offset, MPa	EL%	CVN Impact at -45°C, J
Typical	As Welded	565	490	27	55

PARAMETERS -	PACKING DATA:		
Ø x L, mm 1.6 x 1000 2.0 x 1000 2.4 x 1000	Net Wt., Kg 20 20 20	STORAGE / HANDLING : Keep dry and follow handling instructions mentioned on the box	All Positions

Shielding Gas	Gas Flow Rate, LPM
Ar	10-15

Available in Standard carton packing of 20 kg box, containing 4 plastic tubes of 5 kg each.

ADOR WELDING LIMITED www.adorwelding.com