

ZEDALLOY 350

HARD FACING (Moderate - Abrasion Impact)

ALLOY BASIS

C, Mn, Si, Cr

KEY FEATURES:

- Rutile coated electrode
- Air hardenable deposit
- Machinable with carbide tools
- High weld metal recovery
- Good combination of abrasion and impact properties
- Resistant to friction
- Recommended buffer layer of Tenalloy-16 on hard base materials

APPROVALS: RDSO



TYPICAL APPLICATIONS:

- Excavators, Conveyor parts
- Supporting rollers of Kiln tyres
- Wobbler ends, Cams
- Gear shafts
- Plough shares
- Shear blades
- Girth gears in cement and power plants

MECHANICAL PROPERTIES OF ALL WELD METAL:

Condition	3 Layer, Hardness, HRC (BHN)
As Welded	35-40 (330-380)

PARAMETERS - PACKING DATA:

Ø x L, mm 3.15 x 350 4.0 x 350 5.0 x 450	Amperage, A 100-140 140-180 180-220	 AC (70 V) / DCEN	All Positions, except vertical Downwards 
REDRYING CONDITION: 110°C for ½ hr.			

Available in Standard carton packing of 20 kg box containing 4 cartons of 5 kgs each.

Machinability	Abrasion Resistance	Impact Resistance	Corrosion Resistance
---------------	---------------------	-------------------	----------------------



Physical Properties: With increase in number of squares, property improves